## **IFC-1122**

Acrylic copolymer emulsion



### **Technical Data Sheet**

Name: IFC-1122

Revision Date: 2023-08-03 Version:1.3

#### **Product Description**

IFC-1122 is a low odor hydroxylated acrylic copolymer emulsion. It exhibits excellent chemical resistance, wear restistance and anti-graffiti property when be used with water dispersible polyisocyanate hardeners.

#### **Properties**

- 1. APEO-free, no formaldehyde added
- 2. Excellent chemical resistance, wear resistance
- 3. Applicable in both high gloss and matt varnish systems

#### Characteristic data\*

Property	Value	Unit
Appearance	Milky white liquid	
Solids content	40±1.0	%
PH	7-9	
Viscosity	≤500	mPa∙s
MFFT	13-15	°C
OH Content	Approx. 4.8	%
Density	1.04	g/cm <sup>3</sup>

<sup>\*</sup>These properties are typical but do not constitute specifications.

#### Storage

The product should be stored in dry condition between 5~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

#### **Disclaimer**

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended

# **IFC-1122**



formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.