

IFC-1126

High-performance odor-free interior wall latex paint



Technical Data Sheet

Name: IFC-1126

Revision Date: 2023-08-04

Version:1.3

Product Description

IFC-1126 is a styrene-acrylic copolymer emulsion, using a unique production polymerization process, combined with our unique low-odor environmental protection emulsifier and functional monomer, odor control from the source, and the use of efficient post-treatment process and the latest generation of bi-directional stripping technology process to eliminate residual monomer and VOC, so that the product has a very low emulsion odor, paint odor and construction odor.

Properties

1. Very low VOC content and very low emulsion odor, contribute to the reduction of VOC in coating products;
2. Can be configured with medium to high PVC coatings, with very low paint odor and construction odor and high scrub resistance;
3. Not contain ammonia, APEO, DOP, DBP; no artificially added formaldehyde.

Characteristic data*

Property	Value	Unit
Type	Styrene acrylic copolymer	
Appearance	Milky white & bluish	
Solid content	48±1	%
PH (25 °C)	7.5±1	
Viscosity	300-2000	mPa.s
MFFT	28±2	°C
Particle size	0.1-0.2	µm
Ionicity	Anionic	

*These properties are typical but do not constitute specifications.

Storage

The product should be stored in dry condition between 10~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after shelf life. The

IFC-1126



product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.