## IFC-1206



Pure acrylic emulsion for high solid content and high-gloss exterior paint

### **Technical Data Sheet**

Name: IFC-1206

Revision Date: 2023-08-04 Version:1.3

#### **Product Description**

IFC-1206 is a kind of pure acrylic emulsion with high solid content. It can be formulated to high solid content and high gloss exterior paint. The preparation of gloss can be high as 80 degree Celsius, while system has excellent weather resistance, chemical resistance.

#### **Properties**

- 1. High gloss
- 2. Excellent chemical resistance
- 3. Outstanding weather resistance

#### Characteristic data\*

Property	Value	Unit
Туре	Pure acrylic copolymer	
Appearance	White with blue luster	
PH (25°C)	8±1	
Viscosity	100-1000	
Solid content	60±1	%
MFFT	23	$^{\circ}\! \mathbb{C}$
Particle size	0.2-0.3	μm
Ionicity	Anionic	

<sup>\*</sup>These properties are typical but do not constitute specifications.

#### Storage

The product should be stored in dry condition between 10~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

# IFC-1206



#### Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.