

IFC-1407

Polymer Emulsion for Imitation Stone Paint



Technical Data Sheet

Name: IFC-1407

Revision Date: 2023-07-31

Version:1.3

Product Description

It is the choice of high-quality imported additives and special functional monomers and the use of special synthesis process to synthesize the real stone paint emulsion. It has an outstanding effect of rain resistance, good water whitening resistance and excellent stain resistance. This emulsion can be used for the preparation of environmentally friendly pure acrylic real stone paint and high-glass exterior wall coatings.

Properties

1. Made of silicone propylene.
2. APEO-free.
3. Good film resistance.
4. Excellent resistance to water whitening, rain marks and yellowing.

Characteristic data *

Property	Value	Unit
Polymer Type	Polymer Emulsion	
Appearance	White & light blue milky liquid	
Solid Content	46.0±1.0	%
PH	7.0-9.0	
Viscosity(25°C)	200-2000	mPa·s
MFFT	22	°C
Tg	25	°C
Grain size	0.1-0.2	µm

*These properties are typical but do not constitute specifications.

Storage

The product should be stored in (5-35 °C) airtight containers, preferably in a cool and dry place, avoid exposure to the sun, freezing and high temperature environment. The effective storage period is half a year from the date of packaging.

Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.