

IFC-2833

Polyvinyl Alcohol PVA PVOH Powder



Technical Data Sheet

Name: IFC-2833

Revision Date: 2023-08-04

Version:1.3

Product Description

Polyvinyl alcohol PVA PVOH powder is a non-polluting water-soluble polymer, usually white or slight yellow powder solid. Its performance is between plastic and rubber. It has good adhesion, film-forming ability, insulation, oil resistance, abrasion resistance and gas barrier property, etc.

Properties

1. Good adhesion
2. Excellent film-forming property
3. Good insulation
4. Excellent oil resistance
5. Excellent wear resistance
6. Good gas barrier property

Characteristic data*

Property	Value	Unit
Alcoholysis degree	87-89	mol %
PH	5-7	
Viscosity	87-89	mPa·s
Solid content	99±1	%
Purity	≥93.5	%
Volatile constituent	≤5.0	%
Ash content	≤0.4	%

*These properties are typical but do not constitute specifications.

Storage

The product should be stored in dry condition between 10~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

IFC-2833



Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.