

IFC-7208

Emulsion for PVC floor glue



Technical Data Sheet

Name: IFC-7208

Revision Date: 2023-08-07

Version:1.3

Product Description

IFC-7208 is a flexible acrylate copolymer emulsion. Through the introduction of special cross-linking technology, it provides excellent viscosity and strength of the coating film. It has the characteristics of no APEO and no artificial addition of formaldehyde.

IFC-7208 is designed to be used in PVC floor adhesive. It has excellent initial tack and peeling force, good stickiness, and high bond strength.

Properties

1. Excellent viscosity and strength
2. Excellent initial adhesion and peeling force, good stickiness and high bonding strength
3. Good low temperature performance
4. No APEO and no artificial addition of formaldehyde

Characteristic data*

Property	Value	Unit
Type	Acrylate Copolymer	
Appearance	Milky white with greenish glow liquid	
PH (25 °C)	8±1	
Viscosity	50-450	
Solid content	55.0±1.0	%
MFFT	<0	°C
Ionicity	Anionic	
Grain size	0.2-0.3	µm

*These properties are typical but do not constitute specifications.

Storage

The product should be stored in dry condition between 10~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

IFC-7208



Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.