

# IFCA-2801

Hydrophobic Modified Ethoxylated Urethane



## Technical Data Sheet

Name: IFCA-2801

Revision Date: 2023-08-04

Version:1.3

### Product Description

IFCA-2801 is a nonionic urethane rheology modifier, a suitable thickening agent for any waterborne painting system, especially for architectural coating, industry coating, Wood coatings as well as water-based ink. IFCA-2801 is a high solid content and efficient high-medium shear PU thickener, it allows the formulation of paints with an excellent balance between flow and sag. IFCA-2801 has a rapid thickening response and provides the system excellent flow and leveling. Solvent: water/DGBE. Biocide: (CMIT/MIT = 3:1) 10 ppm, MIT 200 ppm.

### Properties

1. Tin-free, Apeo free
2. Excellent high-medium shear viscosity thickening efficiency
3. Excellent water and alkali resistance
4. Excellent leveling and sag resistance
5. Use over a wide pH range

### Characteristic data\*

Property	Value	Unit
Appearance	Translucent to slightly milky-white liquid	
PH	6.0-9.0	
Viscosity	3000-8000	mPa·s
Density	1.04±0.05	g/cm <sup>3</sup>
Solid content	40±1	%
Chemistry	HEUR	

\*These properties are typical but do not constitute specifications.

# IFCA-2801



## Instructions for use

IFCA-2801 is supplied as a pourable and pumpable liquid, it is easy to use and can be added in any formulation time directly after dilution. Depending on the character and amount of the emulsion as well as filler and pigment, the amount of the addition is variable, probably 0.1-2.0% by weight of the formulation in its supplied form. The exact amount required in each formulation should be determined by pre-trials.

## Storage

The product should be stored in dry condition between 5~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

## Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.