

# IFCA-2836

Redispersible SBR Powder



## Technical Data Sheet

Name: IFCA-2836

Revision Date: 2023-08-04

Version:1.3

### Product Description

Through the design concept of polymer alloy, it is a macromolecular copolymer emulsion synthesized by butadiene and styrene.

It uses a unique protective colloid, redispersible latex powder formed by spray drying.

Polymer Composition: B/S/others

### Properties

- 1.Has good hydrophobicity, alkali resistance and abrasion resistance.
- 2.Excellent adhesion, obviously improving the cohesive strength of the applied product.

### Characteristic data<sup>\*</sup>

Property	Value	Unit
Appearance	White or light yellow powder	
PH	8-10	
Tg	8	°C
Solid content	99±1	%
Density	400-600	g/L
MFFT	5	°C
Ash content	15±2	%

\*These properties are typical but do not constitute specifications.

### Storage

The product should be stored in dry condition between 10~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

# IFCA-2836



## **Disclaimer**

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.