IFC-1215

Styrene-acrylic series



Technical Data Sheet

Name: IFC-1215

Revision Date: 2023-01-10 Version:1.0

Product Description

IFC-9090 is a kind of high scrubbing resistant styrene/acrylate polymer, which is prepared by the polymerization of high quality additives, special technology and functional monomers.

Applications

Suitable for environmental protection interior and exterior wall coatings.

Properties

- 1. Apeo-free
- 2. excellent scrub resistance, good color spread.
- 3. Suitable for high PVC latex paint.
- 4. Resistant to water, alkali and adhesion.
- 5. Pigments and fillers have a strong carrying capacity.

Characteristic data*

Property	Value	Unit
Appearance	White and bluish emulsion	
Solid Content	$50.0 \pm 1.0\%$	%
Viscosity (Brookfield RVT3 # rotor, 30 rpm, 23 ± 0.5 ° C)	5000-10000mPa.s	
PH	7.0-9.0	
Particle Size	0.1-0.2	μm
Lonicity	Anion	
MFT	18℃	

^{*}These properties are typical but do not constitute specifications.

Product safety information

Please refer to material safety data (MSDS) for detailed product safety data, recommended operations and precautions.

IFC-1215



Storage

This product should be kept in a ventilated and dry room to avoid direct sunlight, otherwise it will cause film formation and skin formation of emulsion. It should be transported and stored under the condition of 5 $^{\circ}$ C $^{\sim}$ 35 $^{\circ}$ c. the effective storage period is six months from the date of packing.

Product packaging

1. 50kg plastic barrel 2. 200kg plastic barrel 3. 200kg iron barrel 4. IBC ton barrel.

Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.