

IFC-7330

SBR emulsion



Technical Data Sheet

Name: IFC-7330

Revision Date: 2023-08-04

Version:1.3

Product Description

IFC-7330 is a SBR emulsion for copolymer-cement & mortar. Imported emulsifier and cross-linked monomer are used in the advantage copolymerization of IFC-7330.

Properties

1. The mechanical properties can be improved obviously.
2. High water resistance, but low water permeability
3. Designed especially for cement modified mortar system.
4. Low shrinkage makes the repairing mortar formula easy with high efficiency.
5. Excellent environmentally friendly, low VOC, no formaldehyde

Characteristic data*

Property	Value	Unit
Appearance	Milk white latex	
PH (25 °C)	8±1	
Viscosity	50-300	mPa.s(23°C,3#,60r/m)
Solid content	50±1	%
MFFT	16	°C
Tg	16	°C
Ionicity	Anionic	

*These properties are typical but do not constitute specifications.

Storage

The product should be stored in dry condition between 5~35°C with the integrity of the packaging, and prevented from direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. It is suggested to filter before application and use up once the package is open.

IFC-7330



Disclaimer

Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.