

## Technical Data Sheet

Name: IFC-3121

Revision Date: 2022-07-08

Version:1.3

### Product Description

IFC-3121 is a new self-crosslinking acrylic emulsion prepared from (meth)acrylate as the main raw material. It has properties such as fast drying speed, high gloss, good water resistance, and good compatibility with rust inhibitors and anti-rust pigments and fillers. It can be professionally used in water-based metal primers and metal topcoats in the commercial and industrial protective coating markets.

### Properties

1. It has good early pressure resistance and fast drying speed, suitable for quick drying, stacking needs of water-based coating bottom general varnish and color paint;
2. Good gloss and fullness, white paint gloss up to 95 or more (60° Angle).

### Characteristic data\*

Property	Value	Unit
Appearance	Milky white liquid	/
Solids Content	48±2	%
Viscosity	≤2000	CPS/25℃
Particle Charge	Anion	/
PH	8.5-9.5	/
MFFT	35	℃

\*These properties are typical but do not constitute specifications.

### Application

Suitable for steel structure, fence, road guardrail, industrial parts, trailer, fence, etc.

### Storage

Store in a cool and dry place at 5-30 ℃; Under high temperature or exposure conditions, the shelf life will be significantly shortened; Shelf life of six months from the production date without opening the can.

### Disclaimer

## IFC-3121



Foshan Shunde Infinechem Co., Ltd. recommends that customers should check with Materials Safety Data Sheet (MSDS) for details about safety instructions. We also suggest that you contact the suppliers of other materials used in our recommended formulations and consult appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.